

Typical Viscosity vs. Temperature




Figure 2. Typical Viscosity vs. Temperature of Halocarbon Oils

Modified ASTM D-341
 (Centipoise scale assumes a density of 1.92g/mL)

Kinematic viscosity (centistokes)	Viscosity (centipoise)
10000	19200
5000	9620
3000	5760
2000	3840
1000	1920
500	960
400	768
300	576
200	384
100	192
80	154
60	115
50	96
40	77
30	58
20	38
10	19
9.0	17
8.0	15
7.0	13
6.0	12
5.0	10
4.0	8
3.0	6
2.0	4
1.80	3.5
1.60	3.1
1.40	2.7
1.20	2.3
1.00	1.9
0.90	1.7
0.80	1.5